

Week 8

Light Emitters 1


OLED Basics

Quantifying Efficiency for Displays and Lighting

Fluorescence and Phosphorescence

Thermally Activated Delayed Fluorescence

Chapter 6.1 – 6.3.4, 6.4



Objectives




- Learn about vision: what makes a good display or lighting fixture?
- Gain a knowledge of how fundamental properties of organics leads to arguably the most important organic electronic device: OLEDs
- Learn about challenges yet to be met before OLEDs completely dominate the display market
- Learn about the challenges for lighting

OLEDs


- Basic concepts
- Displays and Lighting
 - R-G-B pixellation
 - WOLEDs
 - TOLEDs
- Getting light out
- Intensity roll-off and annihilation
- Device reliability
- Lasing



Organic Light Emitting Diode (OLED)




electrons and holes
form excitons
(bound e⁻-h⁺ pairs)





Organic Electronics
Stephen R. Forrest


First Polymer OLED



Burroughes, et al. 1990. *Nature*, 347, 539.




Benefits of OLEDs




- Can be prepared on any substrate - active materials are amorphous
- Low cost materials and fabrication methods, scalable to large area
- Readily tuned color and electronic properties *via* chemistry
- Can be transparent when off
- Device characteristics
 - Efficiency $\sim 100\%$ demonstrated, white $> 120 \text{ lm/W}$
 - $> 1,000,000$ hour (100 years) lifetime
 - Can be very bright: 10^6 cd/m^2 , CRT = 100 cd/m^2 , fluorescent panel = 800 cd/m^2
 - Turn-on voltages as low as 3 Volts

OLED vs. Liquid Crystal Displays (LCDs)



Display Technologies


Color Mixing





LCD

OLED
Plasma
CRT



LCD/LED Displays



Two Types of OLED Displays



- RGB pixels
- Top emitting
- Dominates mobile (Samsung)



- WOLED pixels + Color filters
- Top emitting
- Dominates TVs (LG)

Organic Electronics
Stephen R. Forrest

OLED efficiency

$$\eta_{ext} = \eta_{int} \eta_{out} = \gamma \chi_r \phi_p \eta_{out}$$

$\sim 100\%$? $\sim 100\%$ $\sim 20\%$

γ : charge carrier balance factor
ratio of e/h

χ_r : luminescent exciton production

ϕ_p : quantum efficiency of fluorescence

η_{out} : light out-coupling efficiency

1. Fluorescence is restricted to singlet excitons $\chi_r \sim 25\%$

Singlet


$$\frac{1}{\sqrt{2}}(\alpha(\sigma_e) \otimes \beta(\sigma_h) - \alpha(\sigma_h) \otimes \beta(\sigma_e))$$

Triplet

$$\alpha(\sigma_e) \otimes \alpha(\sigma_h)$$

$$\beta(\sigma_e) \otimes \beta(\sigma_h)$$

$$\frac{1}{\sqrt{2}}(\alpha(\sigma_e) \otimes \beta(\sigma_h) + \alpha(\sigma_h) \otimes \beta(\sigma_e))$$





2. Only $\sim 20\%$ of photons are coupled out of OLED devices due to TIR


Maximum Fluorescence External Quantum Efficiency on Glass $\sim 5\%$

Maximum Phosphorescence External Quantum Efficiency on Glass $\sim 25\%$

Today's OLEDs Are Not So Simple



Transparent OLED (TOLED)




- Devices can be > 90% transparent
- Thin metal or electron injection layer is capped with ITO
- Transparent cathode can also be used to prepare top emitting structures
 - OLEDs on metal sheets
 - OLEDs on Si backplanes in AMOLED displays


Bulovic, V., et al. 1996, Nature, 380, 29.



How We See Color: Tri-Stimulus Curves and Chromaticity



Rod & cone cells in retina




Tri-stimulus values

$$X = \int I(\lambda) \bar{x}(\lambda) d\lambda$$

$$Y = \int I(\lambda) \bar{y}(\lambda) d\lambda$$

$$Z = \int I(\lambda) \bar{z}(\lambda) d\lambda$$

$I(\lambda)$ = un-normalized spectral intensity



CIE Coordinates

$$x = \frac{X}{X+Y+Z}; \quad y = \frac{Y}{X+Y+Z}; \quad z = \frac{Z}{X+Y+Z}$$

$$x + y + z = 1 \Rightarrow z = 1 - x - y$$


Scotopic vs. Photopic Vision Response



How things appear at night

Scotopic vision due to the rod cells
– only sense luminosity (brightness)
but not color

(simulation)



How things actually are at night


Photopic, or daytime vision senses color from
cone cells – but not capable at sensing low light
levels

Organic Electronics
Stephen R. Forrest

North wall, Yosemite Valley, CA in March



Limits to color perception









MacAdams Ellipses:

Define the amount of change in color that can be perceived


Each ellipse magnified 10X

Pixel Arrangements for OLED Displays



G. Parthasarathy, et al., *Adv. Mater.*, **11**, 907 (1999).

Various Display Color Gamuts



Radiometric and Photometric Quantities

Radiometric Units				Photometric Units			
Quantity	Symbol	Expression	Unit	Quantity	Symbol	Expression	Unit
Radiant flux	Φ_e		W	Luminance flux	Φ		lm
External quantum efficiency	η_{ext}	$\eta_{int}\eta_{out}$	%	Luminous efficiency	η_L	$\frac{L}{j}$	cd/A
Power efficiency	η_P	$\frac{1}{jV} \frac{d\Phi_e}{dS} = \frac{E_e}{jV}$	%, or W/W	Luminous power efficiency	η_{LP}	$\frac{1}{jV} \frac{d\Phi}{dS} = \frac{E}{jV}$	lm/W
Radiant intensity	I_e	$\frac{d\Phi_e}{d\Omega}$	W/sr	Luminance intensity	L_Ω	$\frac{d\Phi}{d\Omega}$	lm/sr
Radiance	L_e	$\frac{d\Phi_e}{dS d\Omega \cos\theta}$	W/sr-m ²	Luminance	L	$\frac{d\Phi}{dS d\Omega \cos\theta}$	cd/m ² =lm/sr-m ²
Irradiance	E_e	$\frac{d\Phi_e}{dS}$	W/m ²	Illuminance	E	$\frac{d\Phi}{dS}$	lm/m ²
Radiant exitance	M_e	$\frac{d\Phi_e}{dS}$	W/m ²	Luminous exitance	M	$\frac{d\Phi}{dS}$	lm/m ²

Radiometric: Light source properties quantified using standard scientific units

Photometric: Light source properties quantified by visual *perceptive* units



Light source definitions

$$\text{External quantum efficiency} = \frac{\text{No. photons viewed}}{\text{No. of electrons injected}} = \frac{q\lambda P_{\text{meas}}}{(hc) I_{\text{OLED}}}$$

$$\text{Internal quantum efficiency} = \frac{\text{No. photons emitted}}{\text{No. of electrons injected}} = \frac{q\lambda P_{\text{meas}}}{\eta_{\text{out}} (hc) I_{\text{OLED}}}$$

$$\text{Power efficiency} = \frac{\text{Optical power emitted}}{\text{Elect. power injected}} = \frac{P_{\text{meas}}}{I_{\text{OLED}} V_{\text{OLED}}} \quad [\text{W/W}]$$

$$\text{Luminance power efficiency} = \frac{\text{Luminance}}{\text{Elect. power injected}} = \frac{L_{\text{meas}}}{I_{\text{OLED}} V_{\text{OLED}}} \quad [\text{lm/W}]$$

$$\text{Luminance efficiency} = \frac{\text{Luminance}}{\text{Current injected}} = \frac{L_{\text{meas}}}{I_{\text{OLED}}} \quad [\text{cd/A}]$$


Organic Electronics
Stephen R. Forrest

Luminance units: $\text{cd/m}^2 = \text{nits}$; $\text{cd} = \text{lumens}/\pi$ (for a Lambertian source)




Measuring Quantum Efficiency

External QE



- Measure in forward (viewing) direction only
- Mask waveguided and scattered light
- Place OLED on detector for max. accuracy


Internal QE




- Measure using integrating sphere
- Must correct for losses in structure

onics
orrest


Formation dynamics of singlets and triplets




Exciting Dopant Molecules in an OLED




Singlet and triplet formation in OLEDs



Efficiency Improves if Dopant Dispersed in Host





1. Charges trapped on dye molecules
2. Energy transferred from host
3. Effect used to increase color range and efficiency of OLEDs



Energy Transfer from Host to Dopant: A Review


Förster:

- resonant dipole-dipole coupling
- donor and acceptor transitions must be allowed




Electron Exchange (Dexter):

- diffusion of excitons from donor to acceptor by simultaneous charge exchange: short range




spin is conserved: e.g. singlet-singlet or triplet-triplet




Direct trapping on the lumophore



Cation formation by electrical injection



Or, anion formation




Processes can also involve trapping from the host (donor)
Prevalent mechanism for blue PHOLEDs




Energy transfer rates and directions

Forward (exothermic) transfer



- Donor energy > Acceptor energy
- $k_F \sim k_A > k_R, k_D$
- Radiative rate determined by k_A
- Route for red and green emission

Reverse (endothermic) transfer




- Acceptor energy $\sim$ Donor energy
- $k_F \sim k_R > k_A > k_D$
- Radiative rate determined by k_A, k_R
- Route for green and blue emission
- Similar to TADF, delayed fluorescence



100% Internal Efficiency via Spin-Orbit Coupling

Heavy metal induced electrophosphorescence $\sim 100\%$ QE


Baldo, et al., Nature **395**, 151 (1998)



Electrophosphorescent (PHOLED) Device Structure






CBP
(common G,B host)



BCP
(common EBL)


6% PtOEP in CBP

- Exciton blocker increases eff. by 50%
- Roll off at modest luminance levels
- Transfer by trapping




100% Efficient PHOLEDs

Ir(ppy)₂(acac) doped ETL (Triazole)



Adachi, C., et al. 2001. *J. Appl. Phys.*, 90, 5048.

Temperature Independent PL and EL




Lack of dependence on $T \Rightarrow$ No non-radiative recombination
& $\eta_{\text{ext}} \sim 20\% \Rightarrow \eta_{\text{int}} \sim 100\%$

Adachi, C., et al. 2001. *J. Appl. Phys.*, 90, 5048.




Got **Color**? A few metalorganic complexes emitting in the visible




TADF: Another approach to high efficiency

$$\eta_{int} \sim 100\%$$


(a)



4CzPN: R = carbazolyl
2CzPN: R = H




4CzIPN




4CzTPN: R = H
4CzTPN-Me: R = Me
4CzTPN-Ph: R = Ph

(b)




$$k_F \sim k_{ISC,T} \gg k_{ph}$$



TADF Cu-complexes and the Energy Gap Law

(see Ch. 3)





Carbene = MAC*

R, R' = CN (1)
R = CN, R' = H (2)
R, R' = H (3)

Carbene = DAC*



R, R' = CN (4)
R = CN, R' = H (5)
R, R' = H (6)



Au and Ag Complexes also show $\eta_{int} \sim 100\%$

Low voltage high efficiency p-i-n PHOLEDs

Doping p and n transport regions leads to near thermodynamically limited voltage for emission



p-i-n PHOLED Structure

- p-doping by F₄-TCNQ
- n-doping by Li
- **thickness of the CBP/Ir(ppy)₃ emission layer: 5nm**

Low voltage high efficiency p-i-n PHOLEDs

